

XP-002185698

AN - 1993-039771 [05]

**AP - JP19910083802 19910416; [Previous Publ. JP4364120] ; JP19910083802
19910416**

CPY - KOKE

- SUMU

DC - B07

FS - CPI

IC - A61K9/00 ; A61K47/42

MC - B02-V03 B04-B04A6 B12-M11D

M1 - [01] M423 M431 M782 M903 R034 R052 V600 V616 V751 V752

M6 - [02] M903 R034 R052 R112 R525 R527 R531 R534

PA - (KOKE) KOKEN KK

- (SUMU) SUMITOMO SEIYAKU KK

PN - JP3118009B2 B2 20001218 DW200102 A61K9/00 006pp

- JP4364120 A 19921216 DW199305 A61K9/00 006pp

PR - JP19910083802 19910416

XA - C1993-017941

XIC - A61K-009/00 ; A61K-047/42

AB - J04364120 The prepn. is produced by simultaneously extruding (A) 10-40 w/w% collagen and/or gelation soln contg. at least one drug and (B) one or more of 10-40 w/w% collagen and/or gelation soln. or solns either contg. no drug or drugs of different concn. and/or kind from (A), through a multiple nozzle, pref. into gases.

- USE/ADVANTAGE - The prepn. gives a control led release rate, period or drug behavior in vivo and can be industrially produced.

- In an example, 2 w/w% aq. atherocollagen soln. (45g), IFN-alpha (5.6ml, 64, 000, 000 IU) and aq. human serum albumin (1.41ml, 71mg/ml) were blended and lyophilized. The lyophilizate was swollen with water, left in a refrigerator overnight and kneaded in a mortar to give a soln.--(A). Soln. (B) was prepd, from 2 w/w% aq. atherocollagen soln. (90g) and aq. human serum albumin (2.82ml) in a similar manner. Soln. (A) and (B) were separately charged into plastic syringes and defoamed by high-speed centrifuge. They were set to a double nozzle to supply soln, (A) in the central of the nozzle and soln.(B) in the outer layer and them simultaneously extruded at the rate (A) : (B) = 1 : 2 to mould a rod. The rod was dried in a desiccator (RH 75%) for 72 hrs., further in a desiccator with silica gel for 24 hrs. This was cut into pieces to give minipellets (dia. =1.1mm) each contg IFN-alpha (1,000,000 IU(Dwg.0/0))

IW - PRODUCE MULTILAYER COLLAGEN GELATIN PREPARATION SIMULTANEOUS EXTRUDE COLLAGEN GELATIN SOLUTION CONTAIN DRUG COLLAGEN GELATIN SOLUTION CONTAIN NO DRUG DRUG MULTIPLE NOZZLE

IKW - PRODUCE MULTILAYER COLLAGEN GELATIN PREPARATION SIMULTANEOUS EXTRUDE COLLAGEN GELATIN SOLUTION CONTAIN DRUG COLLAGEN GELATIN SOLUTION CONTAIN NO DRUG DRUG MULTIPLE NOZZLE

NC - 001

OPD - 1991-04-16

ORD - 1992-12-16

PAW - (KOKE) KOKEN KK

- (SUMU) SUMITOMO SEIYAKU KK

TI - Prodn. of multilayered collagen and/or gelatin prepn. - by

**simultaneous extrusion of collagen and/or gelatin soln. contg. drug(s)
and collagen and/or gelatin soln. contg. no drug or different drug(s)
using multiple nozzle**